



Texol Grease™ BNT 2

Technical Data Sheet

Texol Grease™ BNT 2

Extreme pressure synthetic inorganic bentonite grease

Product Description

Texol Grease™ BNT 2 Grease is a very unique high temperature grease. The inorganic bentonite thickening system and high quality synthetic base oils and MoS₂ have very good high temperature stability and provide a low coefficient of friction. Texol Grease™ BNT 2 has good extreme pressure properties and provides good bearing protection under heavy loads, shock loads and high temperatures. Texol Grease™ BNT 2 is recommended for use in the temperature range of -20°C to 200°C and intermittently up to +250°C.

Applications and Uses

- Plain and anti-friction bearings
- Lightly loaded gears
- Extreme pressure applications
- Wet and wash-down areas
- Classification KF 2 S-15

Features and Benefits

- Inorganic bentonite thickener
 - Excellent thermal stability
 - Heat, shear and work stability
 - Anti-wear properties
 - Extreme pressure properties
- No gum at high temperature.
Extended lubrication cycles.
Minimal physical changes.
Reduces friction and wear.
Resists shock loads.

General Description

Texol Grease™ BNT 2 Grease is an extreme pressure, water resistant lubricant manufactured with high quality synthetic base oils, an inorganic bentonite thickener and rust and oxidation inhibitors. It provides outstanding film strength, adhesive properties, superior wear protection in heavily loaded and shock-load conditions. This product provides excellent lubrication over a wide range of operating conditions.





Texol Grease™ BNT 2

Technical Data Sheet

Texol Grease™ BNT 2

Extreme pressure synthetic inorganic bentonite grease

Characteristics

NLGI Grade	2	
Penetration, worked (60 strokes) mm/10	280	ASTM D217
Base oil viscosity at 40°C, cSt	460 mm ² /s	ASTM D445
100°C, cSt	48.6 mm ² /s	
Viscosity Index (Base Fluid)	185	ASTM D2270
Base Fluid Type	Synthetic + MoS ₂	
Thickener Type	Inorganic bentonite	
Colour	Black	
Dropping point °C	none	ASTM D2265
4-Ball EP Test, Weld Load, kg	750	ASTM D2596
Useful Temperature Range °C	-20 to 200	



The statements made in this publication are according to our present knowledge. They do not absolve the user from own examinations. A legally binding assurance of certain properties or suitability for a specific use can no be derived from our statements. Possibly existing laws and regulations concerning the handling and use of our products have to be observed by the receiver of our products himself.